

PELADOW® DG CALCIUM CHLORIDE

General Description

Appearance: White, odorless briquettes

Property	Specification Range
Calcium Chloride (wt. %)	88 – 93
<u>Particle Size Distribution</u>	
Retained on ½ in. (12.7 mm) sieve (wt. %)	89 Min.
Passing ¼ in. (6.35 mm) sieve (wt. %)	3 Max.

Typical bulk density is 56 – 64 lb/ft³

Important: The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our current knowledge. NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE, OR WARRANTY OR GUARANTY OF ANY OTHER KIND, EXPRESS OR IMPLIED, IS MADE REGARDING PERFORMANCE, SAFETY, SUITABILITY, STABILITY OR OTHERWISE. This information is not intended to be all-inclusive as to the manner and conditions of use, handling, storage, disposal, and other factors that may involve other or additional legal, environmental, safety or performance considerations, and Occidental Chemical Corporation assumes no liability whatsoever for the use of or reliance upon this information. Appropriate handling and use of the product remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patents or to violate any Federal, State, local or foreign laws.